



Plibrico Company, LLC
 1935 Techny Road - Unit 16
 Northbrook, IL 60062
 (312) 337-9000
 www.plibrico.com

Plibrico Heat Up Schedule

Schedule PS-1 Plicast Castables

Plicast HyMOR, Plicast Super HyMOR, Plicast HyREZIST, Plicast Al-Tuff and Plicast Al-Shield

Heat up rates and hold times will vary with shape configuration and size and furnace loads.

For field installation bake out, please refer to **Schedules B, C, or AT-AS**.

After the castable has cured for 24 hrs., follow the heat up schedule and minimum hold times. Maximum hold temperature will vary with the intended application but should be no lower than 900°F (480°C) to assure thorough shape dewatering.

CAUTION / WARNING

This schedule assumes that heating for bake out is regulated and is applied in a controlled, uniform manner. Note that the target control temperatures are to be measured by thermocouple placement on or within 1/2 in. (12mm) of the hot face surface of the refractory and must be monitored at multiple locations/areas on the refractory within the furnace/vessel. Care should be taken to not exceed the heating rates or cause excessive thermal gradients (>50°F (28°C)) throughout the furnace during bake out. The refractory during bake out must not be exposed to flame impingement or spot (radiant) heating and there should be sufficient combustion air circulation within the furnace.

If the bake out is interrupted due to burner/power failure, care should be taken not to shock the refractory. If/when combustion is restored, the temperature in the furnace should be stabilized at the current temperature before proceeding. Heating should proceed from the point of the schedule corresponding to the current furnace temperature, not the temperature when interruption occurred. Failure to take any of these parameters into account may result in shape damage or explosion.

For questions, please consult your Plibrico representative or the Plibrico Technical or Engineering department.

Schedule PS-1

- All Ramps
@25°F (14°C) / hr (max.)
- Hold @
500°F (260°C)
700°F (350°C)
900°F (480°C) or Max.
- Hold Times (min)
Cross Section

Thickness	Hold
9" (225mm)	8 hr
12" (300mm)	12 hr
18" (460mm)	14 hr

- Cool Down
@ 50°F (28°C) / hr (max.)

