



Plibrico Company, LLC

1935 Techny Road - Unit 16
 Northbrook, IL 60062
 (312) 337-9000
 www.plibrico.com

Technical Data Sheet Pli-Shot HyMOR CL AZS KK

Product # 15411

Available Internationally As: Plico Shotcrete LC CL AZS KK

Product Description:

An alkali resistant, AZS based castable for casting or shotcreting.

Standard Packaging: 55 # / 25 kg Bag

Shelf Life: 6 months

Service Limit: 2800 °F 1540 °C

Contact Limit: N/A °F N/A °C

Bulk Density - In Service: 175 pcf 2804 kg/m³

Bulk Density - To Place: 175 pcf 2804 kg/m³

Minimum Time To Firing: 16 hr

Abrasion Loss after 1500°F / 815°C per ASTM C704

9 cc

Chemistry (calcined) %					
Al ₂ O ₃	51.8	Alk	0.2	MgO	
SiO ₂	19.2	TiO ₂	0.4	ZrO ₂	21.8
CaO	1.6	P ₂ O ₅		Other	
Fe ₂ O ₃	0.3	SiC	4.8		

Water Range Per Standard Package		%	Quarts	Liters
Vib Casting	min			
	max			
Casting	min	6.0	1.6	1.5
	max	7.0	1.9	1.8
Pumping	min	6.4	1.7	1.6
	max	7.6	2.0	1.9

Coefficient of Thermal Expansion (reversible):

3.8 x 10⁻⁶ in/in/°F / 6.8 x 10⁻⁶ mm/mm/°C

Thermal Conductivity	btu*in/hr*ft ² *°F	W/m°C
500°F / 260°C	13.2	1.9
1000°F / 540°C	13.8	2.0
1500°F / 815°C	14.5	2.1
2000°F / 1090°C	15.1	2.2

Temperature		Linear Change% per ASTM C113	CCS per ASTM C133		Cold MOR per ASTM C133		Hot MOR per ASTM C583	
°F	°C		psi	MPa	psi	MPa	psi	MPa
230	110	0.0	8500	59.0	1500	10.3		
1500	820	-0.2	8500	59.0	1700	11.7	2000	13.8
2000	1090	-0.3			2100	14.5	2400	16.6
2500	1370	-0.4			2600	17.9		

Other Data:

Release Date: 1 Aug 2019

Heat Up Guide: Schedule C or C-Linear

ASTM Class: C 401 Class D Regular Castable

Refractory material should be stored in a cool, dry environment.

Note: All data are averaged results of ASTM tests (where applicable) on laboratory specimens. Reasonable variations in data can be expected. Data is not to be used for specification purposes. Product data is periodically updated to reflect product, raw material, process and/or testing changes. Please consult your Plibrico representative to make sure you have the most current data.