



# Plibrico Company, LLC

1935 Techny Road - Unit 16  
 Northbrook, IL 60062  
 (312) 337-9000  
 www.plibrico.com

# Technical Data Sheet Plicast HyMOR 3000 RS KK

Product # 3320

Available Internationally As:

Plico Castable LC 3000 RS KK

### Product Description:

A super duty low cement castable that may be vib cast or cast. Engineered for precast shapes

**Standard Packaging:** 55 # / 25 kg Bag

**Shelf Life:** 6 months

**Service Limit:** 3000 °F 1650 °C

**Contact Limit:** N/A °F N/A °C

**Bulk Density - In Service:** 139 pcf 2227 kg/m<sup>3</sup>

**Bulk Density - To Place:** 139 pcf 2227 kg/m<sup>3</sup>

**Minimum Time To Firing:** 16 hr

**Abrasion Loss after 1500°F / 815°C**  
 per ASTM C704

8 cc

Chemistry (calcined) %					
Al <sub>2</sub> O <sub>3</sub>	48.8	Alk	0.6	MgO	0.1
SiO <sub>2</sub>	45.4	TiO <sub>2</sub>	1.8	ZrO <sub>2</sub>	
CaO	2.5	P <sub>2</sub> O <sub>5</sub>		Other	
Fe <sub>2</sub> O <sub>3</sub>	0.8	SiC			

Water Range Per Standard Package		%	Quarts	Liters
Vib Casting	min			
	max			
Casting	min	7.2	1.9	1.8
	max	7.7	2.0	1.9
Pumping	min			
	max			

**Coefficient of Thermal Expansion (reversible):**

3.1 x 10<sup>-6</sup> in/in/°F / 5.6 x 10<sup>-6</sup> mm/mm/°C

Thermal Conductivity	btu*in/hr*ft <sup>2</sup> *°F	W/m°C
500°F / 260°C	9.3	1.34
1000°F / 540°C	10.0	1.44
1500°F / 815°C	10.7	1.54
2000°F / 1090°C	11.5	1.66

Temperature		Linear Change% per ASTM C113	CCS per ASTM C133		Cold MOR per ASTM C133		Hot MOR per ASTM C583	
°F	°C		psi	MPa	psi	MPa	psi	MPa
230	110	0.0	12500	86.0	1800	12.4		
1500	820	-0.3	11500	79.0	1600	11.0	2200	15.2
2000	1090	-0.4			1900	13.1	2100	14.5
2500	1370	0.6			2000	13.8	400	2.8
3000	1650	-0.4			3000	20.7		

Other Data:

Release Date: 28 Sep 2023

Heat Up Guide: Schedule C or C-Linear

ASTM Class: C 401 Class E

Low Cement Castable

Refractory material should be stored in a cool, dry environment.

**Note:** All data are averaged results of ASTM tests (where applicable) on laboratory specimens. Reasonable variations in data can be expected. Data is not to be used for specification purposes. Product data is periodically updated to reflect product, raw material, process and/or testing changes. Please consult your Plibrico representative to make sure you have the most current data.