



# Plibrico Company, LLC

1935 Techny Road - Unit 16  
 Northbrook, IL 60062  
 (312) 337-9000  
 www.plibrico.com

# Technical Data Sheet Plicast Airlite 26 RS

Product # 3323

Available Internationally As:

Plico Castable Airlite 26 RS

### Product Description:

A lightweight, insulating castable. Low thermal conductivity makes the material a suitable alternative to insulation blocks, allowing it to be poured into place to conform to complex geometries.

**Standard Packaging:** 40 # / 18 kg Bag

**Shelf Life:** 6 months

**Service Limit:** 2600 °F 1430 °C

**Contact Limit:** N/A °F N/A °C

**Bulk Density - In Service:** 25 pcf 401 kg/m<sup>3</sup>

**Bulk Density - To Place:** 25 pcf 401 kg/m<sup>3</sup>

**Minimum Time To Firing:** 24 hr

**Abrasion Loss after 1500°F / 815°C**  
 per ASTM C704

N/A cc

Chemistry (calcined) %					
Al <sub>2</sub> O <sub>3</sub>	51.6	Alk	3.0	MgO	0.7
SiO <sub>2</sub>	32.8	TiO <sub>2</sub>	0.1	ZrO <sub>2</sub>	
CaO	11.0	P <sub>2</sub> O <sub>5</sub>		Other	
Fe <sub>2</sub> O <sub>3</sub>	0.8	SiC			

Water Range Per Standard Package		%	Quarts	Liters
Vib Casting	min			
	max			
Casting	min	140.0	26.9	25.5
	max	150.0	28.8	27.3
Pumping	min			
	max			

**Coefficient of Thermal Expansion (reversible):**

2.3 x 10<sup>-6</sup> in/in/°F / 4.1 x 10<sup>-6</sup> mm/mm/°C

Thermal Conductivity	btu*in/hr*ft <sup>2</sup> *°F	W/m <sup>2</sup> °C
500°F / 260°C	0.8	0.12
1000°F / 540°C	1.0	0.14
1500°F / 815°C	1.1	0.16
2000°F / 1090°C	1.3	0.19

Temperature		Linear Change% per ASTM C113	CCS per ASTM C133		Cold MOR per ASTM C133		Hot MOR per ASTM C583	
°F	°C		psi	MPa	psi	MPa	psi	MPa
230	110	-0.5	180	1.0				
1500	820	-3.5	180	1.0				
2500	1370	-4.4						

Other Data:

Release Date: 1 Nov 2023

Heat Up Guide: Schedule B

ASTM Class: C 401 Class N  
 Insulating Castable

Refractory material should be stored in a cool, dry environment.

**Note:** All data are averaged results of ASTM tests (where applicable) on laboratory specimens. Reasonable variations in data can be expected. Data is not to be used for specification purposes. Product data is periodically updated to reflect product, raw material, process and/or testing changes. Please consult your Plibrico representative to make sure you have the most current data.