



Plibrico Company, LLC

1935 Techny Road - Unit 16
Northbrook, IL 60062
(312) 337-9000
www.plibrico.com

Technical Data Sheet

Pligun 90

Product # 3334

Available Internationally As:

Plico Gun Mix 90

Product Description:

A high alumina, high purity, refractory gun mix.

Standard Packaging: 55 # / 25 kg Bag

Shelf Life: 9 months

Service Limit: 3300 °F 1820 °C

Contact Limit: N/A °F N/A °C

Bulk Density - In Service: 148 pcf 2371 kg/m³

Bulk Density - To Place: 148 pcf 2371 kg/m³

Minimum Time To Firing: 24 hr

Abrasion Loss after 1500°F / 815°C
per ASTM C704

N/A cc

Chemistry (calcined) %

Al ₂ O ₃	90.7	Alk	0.3	MgO	0.1
SiO ₂	3.1	TiO ₂		ZrO ₂	
CaO	5.5	P ₂ O ₅		Other	
Fe ₂ O ₃	0.2	SiC			

Water Range Per Standard Package		%	Quarts	Liters
Vib Casting	min			
	max			
Casting	min			
	max			
Pumping	min			
	max			

Coefficient of Thermal Expansion (reversible):

5.0 x 10⁻⁶ in/in/°F / 9.0 x 10⁻⁶ mm/mm/°C

Thermal Conductivity	btu*in/hr*ft ² *°F	W/m°C
500°F / 260°C	17.0	2.45
1000°F / 540°C	13.5	1.94
1500°F / 815°C	12.0	1.73
2000°F / 1090°C	12.1	1.74

Temperature		Linear Change% per ASTM C113	CCS per ASTM C133		Cold MOR per ASTM C133		Hot MOR per ASTM C583	
°F	°C		psi	MPa	psi	MPa	psi	MPa
230	110	-0.1	3500	24.0	900	6.2		
1500	820	-0.3	3500	24.0	550	3.8	600	4.1
2000	1090	-0.3			600	4.1	550	3.8
2500	1370	-0.9			1200	8.3		
3000	1650	-0.2			2000	13.8		

Other Data:

Release Date: 1 Aug 2024

Heat Up Guide: Schedule B

ASTM Class: C 401 Class G

Low Cement Castable

Refractory material should be stored in a cool, dry environment.

Note: All data are averaged results of ASTM tests (where applicable) on laboratory specimens. Reasonable variations in data can be expected. Data is not to be used for specification purposes. Product data is periodically updated to reflect product, raw material, process and/or testing changes. Please consult your Plibrico representative to make sure you have the most current data.