



Plibrico Company, LLC

1935 Techny Road - Unit 16
 Northbrook, IL 60062
 (312) 337-9000
 www.plibrico.com

Technical Data Sheet Redline Redcon 3000

Product # 51103

Available Internationally As:

Redline Redcon 3000

Product Description:

This super duty, conventionally bonded castable was designed for service conditions at elevated temperatures. It has excellent resistance to chemical attack and abrasion. Typical applications include forge furnaces, process air heaters, flue walls and top caps, heat treating car tops.

Standard Packaging: 55 # / 25 kg Bag

Shelf Life: 12 months

Service Limit: 3000 °F 1650 °C

Contact Limit: N/A °F N/A °C

Bulk Density - In Service: 128 pcf 2051 kg/m³

Bulk Density - To Place: 128 pcf 2051 kg/m³

Minimum Time To Firing:

Water Range Per Standard Package		%	Quarts	Liters
Vib Casting	min	12.0	3.2	3.0
	max			
Casting	min	12.0	3.2	3.0
	max			
Pumping	min			
	max			

Abrasion Loss after 1500°F / 815°C
 per ASTM C704

N/A cc

Chemistry (calcined) %					
Al ₂ O ₃	55.4	Alk	0.7	MgO	0.2
SiO ₂	37.5	TiO ₂	1.3	ZrO ₂	
CaO	3.9	P ₂ O ₅		Other	
Fe ₂ O ₃	1.0	SiC			

Coefficient of Thermal Expansion (reversible):

x 10⁻⁶ in/in/°F / x 10⁻⁶ mm/mm/°C

Thermal Conductivity	btu*in/hr*ft ² *°F	W/m°C
500°F / 260°C	4.8	0.69
1000°F / 540°C	5.7	0.82
1500°F / 815°C	6.9	0.99
2000°F / 1090°C	8.7	1.25

Temperature		Linear Change% per ASTM C113	CCS per ASTM C133		Cold MOR per ASTM C133		Hot MOR per ASTM C583	
°F	°C		psi	MPa	psi	MPa	psi	MPa
250	120	-0.1	3800	26.0	1050	7.2		
1000	540	-0.2			610	4.2		
1500	820	-0.2	3500	24.1	790	5.4		
2000	1090	-0.2			800	5.5		
2500	1370	-0.1			1370	9.4		

Other Data:

Release Date: 1 Aug 1998

Heat Up Guide: Redline Schedule 3

ASTM Class: C 401 Class E
 Regular Castable

Refractory material should be stored in a cool, dry environment.

Note: All data are averaged results of ASTM tests (where applicable) on laboratory specimens. Reasonable variations in data can be expected. Data is not to be used for specification purposes. Product data is periodically updated to reflect product, raw material, process and/or testing changes. Please consult your Plibrico representative to make sure you have the most current data.